



B+BTEc  
 Munterij 8  
 4762 AH Zevenbergen  
 THE NETHERLANDS

Eurofins Product Testing A/S  
 Smedeskovvej 38  
 DK-8464 Galten  
 Denmark

Tel. +45 70 22 42 76  
 Fax +45 70 22 42 75  
 CustomerSupport@eurofins.dk  
 www.eurofins.com/voc-testing

Date  
 21 March 2019  
 Our ref.  
 392-2015-00357601\_15

## Test Report – LEED v4 EQ C (former 4.1), SCAQMD rule 1168 (2005)

### Sample material

Sample identification	<b>BIS-HY GEN2 – Batch no. 67405615 (25.02.2015)</b>
Product type	Multipurpose construction adhesive
Product data, according to manufacturer	Density: 1.765 g/ml at 20 °C ** Water content: 5.56 g/l** Exempt compounds: none ***
Date received	09 November 2015
Analytical period	09 November 2015 – 23 November 2015

### Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty, U <sub>m</sub> (%)
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:

$$([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$$

U<sub>m</sub> (%): The expanded uncertainty U<sub>m</sub> is equal to 2 x RSD%, see also [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty).

### Analytical results

	Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
	98.1	0.3**	0***	28	70*

\* VOC limit for “Multipurpose Construction Adhesive”

\*\* Given by the client

\*\*\* No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

**Morten Sielemann**  
 Analytical Chemist

**Rasmus Stengaard Christensen**  
 Analytical Service Manager, MSc in Chemistry